## 5<sup>TH</sup> REGIONAL SYMPOSIUM ON ELECTROCHEMISTRY SOUTH EAST EUROPE

PROGRAM BOOK OF ABSTRACTS

### 5<sup>TH</sup> REGIONAL SYMPOSIUM ON ELECTROCHEMISTRY SOUTH-EAST EUROPE

**PROGRAM & BOOK OF ABSTRACTS** 

#### PUBLISHED BY

Academician Evgeni Budevski Institute of Electrochemistry and Energy Systems Bulgarian Academy of Sciences 10 Acad. G. Bonchev Str. 1113 Sofia, Bulgaria Tel: (+359 2) 872 25 45 Fax: (+359 2) 872 25 44 www.bas.bg/cleps

PRINTED BY Es Print 49 Kliment Ohridski Blvd. 1756 Sofia, Bulgaria

**EDITORS** 

Daria Vladikova Gergana Raikova

Design

Evgenia Ilkova

Sofia, Bulgaria June 2015

ISBN 978-954-92483-4-0

### 5<sup>TH</sup> REGIONAL SYMPOSIUM ON ELECTROCHEMISTRY SOUTH EAST EUROPE

June 7-11, 2015 RIU Pravets | Pravets, Bulgaria

# PROGRAM BOOK OF ABSTRACTS

Sofia C 2015

#### Microwave Synthesis of Unusually-Shaped Crystalline RuO<sub>2</sub> Supercapacitor

Gavrilo Šekularac<sup>1\*</sup>, Aleksandar Dekanski<sup>1</sup>, Vesna Pavelkić<sup>1</sup>, Sanja Stevanović<sup>1</sup>, Milica Košević<sup>1</sup>, Saša Drmanić<sup>2</sup>, Ivana Kostić<sup>2</sup> and Vladimir Panić<sup>1</sup> <sup>1</sup>Institute of Chemistry, Technology and Metallurgy - Department of Electrochemistry, University of Belgrade, Njegoševa 12, 11001 Belgrade, Serbia <sup>2</sup>Faculty of Technology and Metallurgy, University of Belgrade, Karnagijeva 4, 11020 Belgrade, Srebia \*Corresponding author: gavrilo@ihtm.bg.ac.rs

One-step simple temperature-controlled microwave synthesis was applied to prepare nanocrystalline RuO<sub>2</sub> dispersion from aqueous RuCl<sub>3</sub>. RuO<sub>2</sub> dispersion was subjected to dynamic light scattering in order to analyze the synthesized particles, whereas structural and morphological properties of the solid phase are investigated by AFM, SEM, EDAX and XRD techniques. The ordered unusual shape of ca. 100-nm native particles, as well as highly-ordered prismatic agglomerate sheets are observed. Capacitive properties of RuO<sub>2</sub> was investigated by cyclic voltammetry and electrochemical impedance spectroscopy in 1 M H<sub>2</sub>SO<sub>4</sub> and standard three-electrode cell, with ink-type working electrode on glassy carbon substrate A specific capacitances as high as 750 F/g were obtained, which negligibly depend on sweep rate in 5–500 mV/s range (Fig. 1). These findings are quite unusual for this kind of material consisted of rather large particles [1], and makes it excellent candidate for both low and high power applications. The capacitive response appears stable during prolonged charge/discharge cycling.




Fig.1. Cyclic voltammograms of nanocrystalline RuO<sub>2</sub> in 1 M H<sub>2</sub>SO<sub>4</sub>.

#### References

[1] J. P. Zheng, P. J. Cygan, T.R. Jow, J. Electrochem. Soc. 142 (1995) 2699