



Second Regional Symposium on Electrochemistry

South-East Europe

Program &

Book of Abstracts



Belgrade, Serbia, June 6-10, 2010.

CIP - Каталогизација у публикацији
Народна библиотека Србије, Београд

621.357/.359(048)
541.1(048)
620.193/.197(048)
66.087(048)
543.25(048)

REGIONAL Symposium on Electrochemistry South-East Europe (2 ; 2010 ; Beograd)
Program ; #& #Book of Abstracts / Second Regional Symposium on Electrochemistry
South-East Europe, RSE-SEE, Belgrade, Serbia, June 6-10, 2010. ; [editors Branislav
Nikolić, Vesna Mišković-Stanković, Aleksandar Dekanski]. - Belgrade : Serbian Chemical
Society, 2010 (Belgrade : #Faculty of Technology and Metallurgy, #Development and
Research Center of Graphic Engineering). - XXIII, 170 str. : ilustr. ; 24 cm

Tiraž 270. - Registar.

ISBN 978-86-7132-043-6

a) Електрохемијско инжењерство - Апстракти b) Галванотехника - Апстракти
c) Електрохемија - Апстракти d) Електрохемијске реакције - Апстракти e)
Антикорозиона заштита - Апстракти f) Аналитичка електрохемија – Апстракти

COBISS.SR-ID 175352076

*SECOND REGIONAL SYMPOSIUM ON ELECTROCHEMISTRY : : SOUTH-EAST EUROPE
BELGRADE, SERBIA, JUNE 6-10, 2010*

PROGRAM & BOOK OF ABSTRACTS

Published by

Serbian Chemical Society, Karnegijeva 4/III, PAK 135804, 11120 Belgrade, SERBIA
phone./fax: +381 11 3370 467; www.shd.org.rs, E-mail: Office@shd.org.rs

For Publisher

Ivanka POPOVIĆ, Prezident of the Society

Editors

Branislav NIKOLIĆ

Vesna MIŠKOVIĆ-STANKOVIĆ

Aleksandar DEKANSKI

Cover Design, Page Making and Computer Layout

Aleksandar DEKANSKI

Circulation:

270 Copy Printing

ISBN 978-86-7132-043-6

Printing:

Development and Research Center of Graphic Engineering,

Faculty of Technology and Metallurgy, Karnegijeva 4, PAK 135804, 11120 Belgrade, SERBIA



POSTER PRESENTATIONS

ECS-P-01

Electrochemical performance of $\text{Li}_{1.2}\text{V}_3\text{O}_8$ in saturated aqueous solution of LiNO_3

Ivana Stojković, Nikola Cvjetičanin, Vladimir Pavlović*, Slavko Mentus
*University of Belgrade, Faculty of Physical Chemistry, Studentski Trg 12-16
Belgrade, Serbia*

**Institute of Technical Sciences of SASA, Knez-Mihailova 35/IV, 11000 Belgrade, Serbia*

The $\text{Li}_{1.2}\text{V}_3\text{O}_8$ was synthesized by modified sol-gel method and treated at several temperatures. Electrochemical performance of $\text{Li}_{1.2}\text{V}_3\text{O}_8$ was investigated by galvanostatic cycling in saturated aqueous solution of LiNO_3 . The sample treated at 300 °C consisted of uniform rod-shaped particles, 100–150 nm in diameter and 300–800 nm in length. It displayed the best electrochemical performance: the initial discharge capacity amounted to 136.8 mAhg^{-1} and capacity fade upon 50 charging/discharging cycles was only 12 %. This is significant improvement compared to the product obtained by solid state reaction, published by other authors. There is the literature evidence that $\text{Li}_{1.2}\text{V}_3\text{O}_8$ synthesized in similar way displays enhanced electrochemical properties in organic solutions, too.

ECS-P-02

Oxidation of formic acid on bulk and nanosized Pt-Co alloys

Maja D. Obradović, Amalija V. Tripković, Snežana Lj. Gojković*
*Institute of Chemistry, Technology and Metallurgy, University of Belgrade, Njegoševa 12,
P.O. Box 473, 11000 Belgrade, Serbia*

**Faculty of Technology and Metallurgy, University of Belgrade, Karnegijeva 4,
P.O. Box 3503, 11000 Belgrade, Serbia*

Bulk Pt_3Co and nanosized Pt_3Co and PtCo alloys supported on XC-72 high area carbon were investigated as the electrocatalysts for the oxidation of formic acid. Cyclic voltammetry in 0.1 M HClO_4 and stripping voltammetry of CO_{ads} in the same electrolyte show a small difference in the potentials of Pt-oxide formation and reduction and CO_{ads} oxidation. Based on these results, we concluded that electronic modification of Pt by Co atoms, which was theoretically predicted and experimentally proved on solid/gas interface, is exhibited in the electrochemical environment. Promotion of HCOOH oxidation rate on bimetallic Pt-Co surfaces with respect to pure Pt was found to be up to factor of eight in the case of PtCo/XC-72 catalyst. This moderate increase of the reaction rate is ascribed mostly to the ensemble effect, because partial leaching of Co increased Pt:Co ratio at the bimetallic surfaces, diminishing the efficiency of the ensemble effect.